

### Technical Information

INOFLON<sup>®</sup> GN7003 is polymerized in an aqueous dispersion medium to produce agglomerated fine dispersion resin. It is designed for low reduction ratio applications. INOFLON<sup>®</sup> GN7003 grade is suitable for electrical tape, big diameter liners, yarn, dental floss, membrane and fibers, etc.

### Technical Information

- ◆ High chemical resistance
- ◆ High molecular weight
- ◆ High green strength
- ◆ High stretch ratio
- ◆ Processable by standard paste extrusion process
- ◆ PFOA Free

### Typical Properties of INOFLON<sup>®</sup> GN7003

Properties	Test Method	Unit	Nominal Value
<b>Powder properties</b>			
Bulk density	ASTM D 4895	g/l	500
Average particle size (d <sub>50</sub> )	ASTM D 4895	μm	525
<b>Processing</b>			
Extrusion pressure (Reduction ratio 400:1)	ASTM D 4895	MPa(psi)	42 (6092)
<b>Mechanical properties</b>			
Std. specific gravity (SSG)	ASTM D 4895	-	2.155
Tensile strength	ASTM D 4895	MPa(psi)	33 (4786)
Elongation	ASTM D 4895	%	330

Note: These are typical properties and not to be used for specification purpose

### FDA Compliance

When products made from INOFLON<sup>®</sup> GN7003 are correctly processed, that is sintered at high temperature practiced by industries, they may comply with FDA Regulation 21 CFR 177.1550 for use in contact with food.

### Packaging

INOFLON<sup>®</sup> GN7003 is packed in 25Kgs plastic drums.

### Handling and storage

INOFLON<sup>®</sup> GN7003 is susceptible to shear damage, particularly above its transition point 19°C (66.2°F). Handling and transportation of the containers could easily subject the powder to sufficient shear to spoil it if the resin temperature is above transition point. To ensure that the resin does not fibrillate, it should be cooled below its transition temperature prior to handling and transportation. A typical commercial container (20–30 kg) should be cooled 24–48 hours to <15°C (59°F) to assure temperature uniformity throughout the container. Specially designed shallow cylindrical drums are used to minimize lump formation, compaction, and shearing of the resin. To prevent moisture contamination, the drum must not be opened where the ambient dew point is above the temperature of resin to avoid immediate condensation on the resin. Storage and handling facilities should be clean. Very small foreign particle are highly visible in the white resin, keep resin drum closed and clean. Good housekeeping and careful handling are essential.

## Processing

INOFLON® GN7003 is fabricated by paste extrusion, where PTFE powder is first blended at temperatures below 19°C (66.2°F) with a hydrocarbon lubricant which acts as an extrusion aid. After ageing at about 30°C (86°F) it is then formed into a cylindrical preform at a fairly low pressure and placed inside the barrel of a paste extruder where it is forced through a die with a constant extrusion rate at 30–50°C (86–122°F). The extrudate is passed through multiple ovens and a cooling device where it is first dried, then sintered, and finally cooled. Drying and sintering can be performed continuously “in line” with the extrusion or in separate drying and sintering ovens.

## Safety precautions

Handling and processing of PTFE must be done in ventilated area to prevent personnel exposure to the fumes liberated during sintering and heating of the resin. Fumes must not be inhaled and eye and skin contact should be avoided. In case of eye contact flush, with water immediately and seek medical help. Smoking tobacco or cigarettes contaminated with PTFE may result in a flu-like condition including chills, fever and sore throat that may not start until a few hours after exposure has taken place. These symptoms usually pass within about 24 hours. Vapors and gases generated by PTFE during sintering must be completely removed from the factory areas.

Mixtures of some metal powders such as magnesium or aluminum are flammable and explosive under some conditions. Please read the Material Safety Data Sheet and the detailed information in the “Guide to the Safe Handling of Fluoropolymer Resins” published by the fluoropolymer division of the Society of the Plastic Industries available at [www.fluoropolymers.org](http://www.fluoropolymers.org)

INOFLON® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resin. INOFLON® can be used in applications duly approved by GFL. Customers who plan to use the word INOFLON® as the trade mark on or relation to their own fluoropolymer parts and other products in any style or combination or in any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain INOFLON® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and insure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of use of this information for application of its INOFLON® branded Fluoropolymer resin and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

**Note warning:** Do not use any of INOFLON® PTFE resins in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

For more information, please contact Gujarat Fluorochemicals Limited

### Corporate & Marketing Office

Gujarat Fluorochemicals Ltd.

Inox Towers, Plot No. 17 Sector 16A, Noida- 201301 U.P., India

T: +91-120-6149600 F: +91-120-6149610

W: [www.inoflon.com](http://www.inoflon.com) E: [Inoflon@gfl.co.in](mailto:Inoflon@gfl.co.in)

### Works

12/A, GIDC Dahej Industrial Estate, Tehsil Vagra, Distt. Bharuch-392130, Gujarat, INDIA

W: [www.inoflon.com](http://www.inoflon.com) E: [inoflon@gfl.co.in](mailto:inoflon@gfl.co.in)

### Germany

Gujarat Fluorochemicals

GmbH, Chilehaus A, Fischertwiete 2 Hamburg - 20095, Germany

### USA

GFL America, LLC, 352 N, US Highway 77, Rockdale, Texas 76567, USA