

### Technical Information

INOFLON<sup>®</sup> PFA 8910 is a melt processable of fine PFA particles aqueous dispersion. It can be used for coating system of high performance non-stick coatings and impregnation of woven packing, yarn & glass fabric in combination with PTFE dispersions.

### Product Features

- ◆ Good weldability
- ◆ Excellent film forming properties
- ◆ Excellent chemical resistance
- ◆ Low abrasion
- ◆ Wide service temperature range from -200 °C to +260 °C
- ◆ Good non-stick properties

### Typical Properties of INOFLON<sup>®</sup> PFA 8910

Properties	Test Method	Unit	Nominal Value
Solid content (% PFA resin by weight)	ASTM D4441/DIN EN ISO 12086	%	50
Surfactant content on PFA solids	ASTM D4441/DIN EN ISO 12086	%	6
Specific gravity	ASTM D4441/DIN EN ISO 12086	-	1.40
Average particle size	INTERNAL	nm	150
pH of dispersion	ASTM E70/DIN ISO 976	-	>9.5
Melt Flow Rate	ASTM D1238	g/10min	2
Melting Point	ASTM D4591	°C (°F)	310 (590)

Note: These are typical properties and not to be used for specification purpose

### FDA Compliance

When products made from INOFLON<sup>®</sup> PFA 8910 are correctly processed, that is sintered at high temperature practiced by industries, they may comply with FDA Regulation 21 CFR 177.1550 for use in contact with food.

Note- Unsintered dispersion products do not comply.

### Packaging

INOFLON<sup>®</sup> PFA 8910 is available in 30 litre (7.9 gal) non returnable plastic drum and 1000 litre (264 gal) IBC recyclable containers.

## Handling and Storage

Aqueous dispersions should be stored at temperatures between 10°C to 25°C. Freezing the dispersion or storage of dispersion at high temperature must be avoided due to its irreversible coagulating effect on PFA particles. Aqueous dispersions have a low settling tendency although if the dispersions are to be stored for a long duration, it should be rolled or gently agitated twice a month or before usage to rejuvenate settled particles.

Ammonium hydroxide is used by GFL to maintain the pH of dispersion between 9.5 and 10.5 at the time of shipment. High ambient temperatures can deplete the ammonia level and reduce the pH which favors bacterial growth in dispersion and can cause odor and scum. The pH should be monitored and maintained between 9.5 to 10.5.

Please also read our Material handling and Storage guide for more information

## Safety precautions

Handling and processing of PFA must be done in ventilated areas to prevent personnel exposure to the fumes liberated during sintering and heating of the resin. Fumes should not be inhaled and eye and skin contact must be avoided. In case of skin contact wash with soap and water immediately. In case of eye contact, flush with water immediately and seek medical help. Smoking tobacco or cigarettes contaminated with PFA may result in a flu-like condition including chills, fever and sore throat that may not occur until a few hours after exposure has taken place.

Mixtures of some metal powders such as magnesium or aluminum are flammable and explosive under some conditions. Please read the Material Safety Data Sheet and the detailed information in the "Guide to the safe handling of Fluoropolymer Resins" published by the Fluoropolymer Division of The Society of the Plastics Industry available at [www.plasticseurope.org](http://www.plasticseurope.org)

INOFLON® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resin. INOFLON® can be used in applications duly approved by GFL. Customers who plan to use the word INOFLON® as the trade mark on or relation to their own fluoropolymer parts and other products in any style or combination or in any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain INOFLON® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and insure that their specific conditions of processing present no health or safety hazards. GFL does not warrant, either expressly or impliedly in respect of use of this information for application of its INOFLON® branded Fluoropolymer resin and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

**Note warning:** Do not use any of INOFLON® FEP resins in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

For more information, please contact Gujarat Fluorochemicals Limited

### Corporate & Marketing Office

Gujarat Fluorochemicals Ltd.  
Inox Towers, Plot No. 17, Sector 16A, Noida- 201301 U.P., India  
Tel: +91-120-6149600 Fax: +91-120-6149610  
[www.inoflon.com](http://www.inoflon.com)      [Inoflon@gfl.co.in](mailto:Inoflon@gfl.co.in)

### Works

12/A, GIDC Dahej Industrial Estate, Tehsil Vagra, Distt. Bharuch-392130, Gujarat, INDIA

### Germany

Gujarat Fluorochemicals GmbH  
Chilehaus A, Fischertwiete 2 Hamburg - 20095, Germany  
Tel: +49-40-32005118/119

### USA

GFL America, LLC, 352 N, US Highway 77, Rockdale, Texas 76567, USA  
Tel: +1-512-446-770