

## PFA 8115PT

### TECHNICAL DATA SHEET

#### TECHNICAL INFORMATION

INOFLON® PFA 8115PT is a melt-processable fluoroplastic resin available in powder form. PFA 8103PT powder is specially designed for use in powder coating applications.

#### PRODUCT FEATURES

- Smooth surfaces
- Excellent chemical resistance
- Service temperature up to 260°C (500°F)
- Good electrical insulation and mechanical properties
- Excellent non-stick performance
- Good transparency
- Good electrostatics and fluidization

#### TYPICAL PROPERTIES

Properties	Test Method	Unit	Nominal Value
Melt Flow Rate	ASTM D 1238	g/10 min	10
Mean particle size	-	µm	25
Bulk density	ASTM D 1895	g/l	500
Specific gravity	ASTM D 792	-	2.15
Melting points	ASTM D 4591	°C (°F)	308 (586)
Tensile strength	ASTM D 3307	MPa (psi)	25 (3626)
Elongation	ASTM D 3307	%	275

Note: These are typical properties and not to be used for specification purposes.

#### FDA COMPLIANCE

INOFLON® PFA complies with FDA Regulation 21CFR 177.1550 and when products made from INOFLON® PFA 8115PT are correctly processed, that is sintered at high temperature practiced by industries, they may comply with FDA Regulation 21CFR 177.1550 for use in contact with food.

#### PACKAGING

INOFLON® PFA 8115PT powder is supplied in 25 kg quantities.

# INOFLON® PFA 8115PT

## HANDLING AND STORAGE

INOFLON® PFA 8115PT can be stored for a relatively long period of time provided they are stored in a clean place, dry place and protected by direct sunlight and possible contamination.

## PROCESSING

INOFLON® PFA 8115PT powder is processed by coating.

## SAFETY PRECAUTIONS

Handling and processing of PFA must be done in ventilated areas to prevent personnel exposure to the fumes liberated during sintering and heating of the resin. Fumes should not be inhaled and eye and skin contact must be avoided. In case of skin contact wash with soap and water immediately. In case of eye contact, flush with water immediately and seek medical help. Smoking tobacco or cigarettes contaminated with PFA may result in a flu-like condition including chills, fever and sore throat that may not occur until a few hours after exposure has taken place. Mixtures of some metal powders such as magnesium or aluminum are flammable and explosive under some conditions. Please read the Material Safety Data Sheet and the detailed information in the "Guide for the Safe Handling of Fluoropolymer Resins" available at [www.plasticseurope.org](http://www.plasticseurope.org).

INOFLON® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resin. INOFLON® can be used in applications duly approved by GFL. Customers who plan to use the word INOFLON® as the trademark on or relation to their fluoropolymer parts and other products in any style or combination or any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain INOFLON® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on the information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and ensure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of the use of this information for application of its INOFLON® branded fluoropolymer resin and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

WARNING: Do not use any of INOFLON® PFA resins in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

## SALES AND TECHNICAL SUPPORT

### Corporate & Marketing Headquarter

Gujarat Fluorochemicals Limited  
INOX Towers, 17, Sector-16A,  
Noida - 201301 U.P., India  
+91 120 6149600

### Europe

Gujarat Fluorochemicals GmbH  
Regus Center Watermark 14<sup>th</sup> Floor,  
Überseeallee 10, 20457 Hamburg, Germany  
+49 40 808074-667/668

### Works

Gujarat Fluorochemicals Limited  
12/A Dahej, GIDC, Industrial Estate,  
Tehsil Vagra, Dist. Bharuch 392130, Gujarat, India  
+91 2641 618003

### Americas

GFL Americas, LLC  
1212 Corporate Dr., Suite-540,  
Irving, TX 75038, USA  
+1 512 446 7700

