

## AD9300EX

### TECHNICAL DATA SHEET

#### TECHNICAL INFORMATION

INOFLON® AD9300EX is an aqueous milky dispersion of PTFE resin, stabilized in water by non-ionic surfactant. INOFLON® AD9300EX is a general-purpose product; it can be used for impregnation of woven packing, yarns, glass fabric for food and industrial market, and some metal coating application, also used as an anti-drip additive for plastic. It provides the excellent properties of PTFE resins to porous structures and also to base materials when used as an additive.

#### PRODUCT FEATURES

- Excellent chemical resistance
- Service temperature: -250°(-418°F) to +250°(482°F)
- Excellent wetting properties
- Excellent wetting properties
- Excellent film forming properties
- High shear stability
- Product is manufactured without the use of fluorinated polymerization aids

#### TYPICAL PROPERTIES

Properties	Test Method	Unit	Nominal Value
Solid content (% PTFE resin by weight)	ASTM D4441/DIN EN ISO 12086	%	60
Surfactant content on PTFE solids	ASTM D4441/DIN EN ISO 12086	%	6.5
Specific gravity	ASTM D4441/DIN EN ISO 12086	-	1.51
Average particle size	GFL Internal Method	nm	230
pH of dispersion	ASTM E70/DIN ISO 976	-	>9.5

Note: These are typical properties and not to be used for specification purposes.

#### FDA COMPLIANCE

When products made from INOFLON® AD9300EX are correctly processed, that is sintered at high temperature practiced by industries, they may comply with FDA Regulation 21 CFR 177.1550 for use in contact with food.

NOTE - Unsintered dispersion products do not comply.

#### PACKAGING

INOFLON® AD9300EX is available in 30 Litre (7.9 gal) non-returnable plastic drum and 1000 Litre (264 gal) recyclable IBC.

# AD9300EX

## HANDLING AND STORAGE

Aqueous dispersions should be stored at temperatures between 10°C and 25°C. Freezing the dispersion or storage of dispersion at high temperatures must be avoided due to its irreversible coagulating effect on PTFE particles. Aqueous dispersions have a low settling tendency although if the dispersions are to be stored for a long duration, it should be rolled or gently agitated twice a month or before usage to rejuvenate settled particles.

Ammonium hydroxide is used by GFL to maintain the pH of dispersion between 9.5 and 10.5 at the time of shipment. High ambient temperatures can deplete the ammonia level and reduce the pH which favors bacterial growth in dispersion and can cause odor and scum. The pH should be monitored and maintained between 9.5 and 10.5.

Please also read our Material Safety Data Sheet for more information..

## SAFETY PRECAUTIONS

Handling and processing of PTFE must be done in ventilated areas to prevent personnel exposure to the fumes liberated during sintering and heating of the resin. Fumes should not be inhaled and eye and skin contact must be avoided. In case of skin contact, wash with soap and water immediately. In case of eye contact, flush with water immediately and seek medical help. Smoking tobacco or cigarettes contaminated with PTFE may result in a flu-like condition including chills, fever and sore throat that may not occur until a few hours after exposure has taken place.

Mixtures of some metal powders such as magnesium or aluminum are flammable and explosive under some conditions. Please read the Material Safety Data Sheet and the detailed information in the "Guide for the

Safe Handling of Fluoropolymer Resins" available at [www.plasticseurope.org](http://www.plasticseurope.org).

INOFロン® is the brand name of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resin. INOFロン® can be used in applications duly approved by GFL. Customers who plan to use the word INOFロン® as the trademark on or relation to their fluoropolymer parts and other products in any style or combination or any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL fluoropolymer resin is permitted to claim that their products contain INOFロン® without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on the information and technical data that Gujarat Fluorochemicals Limited believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and ensure that their specific conditions of processing present no health or safety hazards. GFL does not warranty, either expressly or impliedly in respect of the use of this information for application of its INOFロン® branded fluoropolymer resin and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as a grant of license by GFL to operate under or a recommendation to infringe any patents.

WARNING: Do not use any of INOFロン® PTFE resins in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought. WARNING: Do not use any of INOFロン® PTFE resins in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.

## SALES AND TECHNICAL SUPPORT

### Corporate & Marketing office:

#### Gujarat Fluorochemicals Limited

Inox Towers, Plot no. 17, Sector 16/A

Noida-202301, U.P., INDIA

Tel: +91-120-6149600

Fax: +91-120-6149610

### Europe

#### Gujarat Fluorochemicals GmbH

Esplanade 40, 9<sup>th</sup> Floor

20354 Hamburg, Germany

+49 040 5582 395- 80

### Works

#### Gujarat Fluorochemicals Limited

12/A, GIDC Dahej Industrial Estate.

Tehsil- Vagra, Distt. Bharuch-392230, Gujarat, INDIA

Website: [www.fluonox.co.in](http://www.fluonox.co.in); [www.gfl.co.in](http://www.gfl.co.in)

Email: [contact@gfl.co.in](mailto:contact@gfl.co.in)

### Americas

#### GFL Americas, LLC

1212 Corporate Dr., Suite-540,

Irving, TX 75038, USA

+1 512 446 7700

